

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the present application.

***Listing of Claims:***

1. **(Currently Amended)** A polyamide resin composition comprising 100 parts by weight of a polyamide resin component (A) and 0.01 to 5 parts by weight of a metallic soap component (B), wherein:

the polyamide resin component (A) comprises:

a dicarboxylic acid component (a-1), which comprises a terephthalic acid component, and an aromatic dicarboxylic acid component other than the terephthalic acid component and/or an aliphatic dicarboxylic acid component of 4 to 20 carbon atoms, and

a diamine component (a-2) comprising an aliphatic diamine component; and

the metallic soap component (B) comprises a ~~metallic soap comprising an aliphatic carboxylic acid of 20 to 25 carbon atoms and a monovalent or divalent metal salt.~~ monovalent or divalent metal salt of an aliphatic carboxylic acid of 20 to 25 carbon atoms.

2. **(Original)** The polyamide resin composition as claimed in claim 1, wherein the polyamide resin component (A) has an intrinsic viscosity, as measured in 96.5% sulfuric acid at 25°C, of 0.5 to 3.0 dl/g and a melting point, as measured by a differential scanning calorimeter (DSC), of 280 to 330°C.

3. **(Currently Amended)** The polyamide resin composition as claimed in claim 1 or claim 2, which further contains ~~a filler~~ at least one filler selected from the group consisting of a flame retardant, flame retarding assistant, metal salt of aliphatic carboxylic acids of 26 to 32 carbon atoms as a lubricant, silica, alumina, calcium carbonate, titanium dioxide, talc, wollastonite, diatomaceous earth, clay, kaolin, spherical glass, mica, magnesium oxide, zinc oxide, potassium titanate, whisker, glass fiber, potassium titanate fiber, metal coated glass fiber, ceramic fiber, fibrous wollastonite, metal carbide fiber, cured metal fiber, asbestos fiber, boron fiber, aramid fiber and carbon fiber, in an amount of 1 to 300 parts by weight based on 100 parts by weight of the polyamide resin component (A).

4. **(Currently Amended)** The polyamide resin composition as claimed in claim 3, wherein ~~the~~ said filler comprises ~~a glass~~ the

Application No. 10/607,519

Art Unit 1711

Reply to Office Action of September 28, 2004

glass fiber, ~~a flame~~ the flame retardant, ~~a flame~~ the flame  
retarding assistant ~~and a~~ and the lubricant.

5. **(Currently Amended)** A molded article comprising the  
polyamide resin composition of ~~any one of claims 1 to 4.~~ claim 1 or  
2.

6. **(New)** The polyamide resin composition as claimed in claim  
1, wherein said aliphatic carboxylic acid of 20 to 25 carbon atoms  
in component (B) is at least one selected from the group consisting  
of arachic acid, behenic acid, lignoceric acid and pentacosanoic  
acid.